



Recycled Content of H-Shield

CALCULATED BY WEIGHT

888.746.1114

Foam Thickness	Total Recycled %	Post Consumer Recycled %	Pre Consumer (Post Industrial) Recycled %
1.0	37.80%	27.80%	10.00%
1.1	36.20%	26.20%	10.00%
1.2	34.50%	24.60%	9.90%
1.3	33.20%	23.30%	9.90%
1.4	31.90%	22.10%	9.80%
1.5	30.80%	21.00%	9.80%
1.6	29.70%	20.00%	9.70%
1.7	28.80%	19.10%	9.70%
1.8	28.00%	18.30%	9.70%
1.9	27.20%	17.50%	9.70%
2.0	26.50%	16.90%	9.60%
2.1	25.80%	16.20%	9.60%
2.2	25.20%	15.60%	9.60%
2.3	24.70%	15.10%	9.60%
2.4	24.20%	14.60%	9.60%
2.5	23.60%	14.10%	9.50%
2.6	23.10%	13.60%	9.50%
2.7	22.70%	13.20%	9.50%
2.8	22.30%	12.80%	9.50%
2.9	21.90%	12.40%	9.50%
3.0	21.60%	12.10%	9.50%
3.1	21.10%	11.70%	9.40%
3.2	20.80%	11.40%	9.40%
3.3	20.50%	11.10%	9.40%
3.4	20.30%	10.90%	9.40%
3.5	20.00%	10.60%	9.40%
3.6	19.70%	10.30%	9.40%
3.7	19.50%	10.10%	9.40%
3.8	19.30%	9.90%	9.40%
3.9	19.00%	9.60%	9.40%
4.0	18.80%	9.40%	9.40%
4.5	17.80%	8.50%	9.30%

POST CONSUMER RECYCLED CONTENT...

Is consumer waste that has become a raw material (feedstock) for another product (ie glass, plastic, aluminum cans etc...)

PRE CONSUMER - FORMALLY KNOWN AS POST INDUSTRIAL RECYCLED CONTENT...

Is output from a process that has not been used as part of a consumer product, that is sold, traded or exchanged under commercial terms as feedstock for another industrial process, and that would have otherwise be landfilled, incinerated or somehow disposed of as a waste.